

Re-Tek Products
 3320 Cleaton Road
 Central City, KY 42330
 Phone (502) 426-2677
 Fax (502) 415-7299

PRODUCT DATA SHEET

Product: .5-1.5 mm Red EPDM

Product Description: Granulated peroxide cured Red EPDM sheet stock.
 Specific Gravity: 1.55
 Shore Hardness: 60 +/- 5.

Chemical Properties	PRODUCT ANALYSIS		TEST METHOD
	Min.	Max.	D-297
Acetone Extract	10.0	22.0	
Ash Content	35.0	65.0	
Carbon Black Content	---	--	Difference
Rubber Hydrocarbon	25.0	40.0	

Physical Properties	U.S Standard Screen	% Retained	D-1511
Sieve Analysis	-----	-----	
	10 Mesh	0-5%	
	16 Mesh	60-85%	
	20 Mesh	10-30%	
	Pan	0-5%	
	Specific Gravity -- 1.55 +/- .03		D-297
	Moisture : 1% Maximum		D-1509
	Bulk Density: Approx. 42 lbs. / cu. ft		
	Free Flowing Agent Additive: 2% / Wght. Max.		

A Guideline Specification Only. Provided for the review and approval of a design professional to determine the proper use and suitability of this material for the installed use and purpose intended.